

**This page Is Inserted by IFW Operations
And is not part of the Official Record**

BEST AVAILABLE IMAGES

**Defective images within this document are accurate representations of
The original documents submitted by the applicant.**

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
Please do not report the images to the
Image Problem Mailbox.**

PRODUCTION OF LIQUID CRYSTAL ELEMENT

Patent Number: JP61007822
Publication date: 1986-01-14
Inventor(s): OKADA SHINJIROU
Applicant(s): CANON KK
Requested Patent: ☐ JP61007822
Application Number: JP19840127407 19840622
Priority Number(s):
IPC Classification: G02F1/133
EC Classification:
Equivalents:

Abstract

PURPOSE: To form stably the spacing between electrode substrates as small as 1-2 μ m by forming a spacer part to the central part of the electrode substrates then printing an adhesive agent thereto and adhering and fixing a pair of the electrode substrates together with the adhesive agent at the circumferential edge.

CONSTITUTION: The spacer member 25 consisting of a polyimide resin is formed by using a lithographic film forming technique on either one of a pair of the transparent substrates 22a, 22b. Adhesive agent stripes are printed and formed by screen or offset printing, etc. on the member 25. A pair of the substrates 22a, 22b are adhered and fixed together with the adhesive agent 27 at the circumferential edge. The film forming technique controllable in the thickness of an Angstrom unit is utilized in the stage of forming the member 25 and therefore the uniform and stable inter-substrate spacing is formed even if said spacing is as small as 1-2 μ m.

Data supplied from the esp@cenet database - I2

⑨ 日本国特許庁(JP)

⑩ 特許出願公開

⑫ 公開特許公報(A) 昭61-7822

⑤ Int. Cl.¹

識別記号

庁内整理番号

⑬ 公開 昭和61年(1986)1月14日

G 02 F 1/133

1 2 3

8205-2H

審査請求 未請求 発明の数 1 (全4頁)

⑭ 発明の名称 液晶素子の製造方法

⑯ 特 願 昭59-127407

⑰ 出 願 昭59(1984)6月22日

⑱ 発 明 者 岡 田 伸 二 郎 東京都大田区下丸子3丁目30番2号 キャノン株式会社内
 ⑲ 出 願 人 キャノン株式会社 東京都大田区下丸子3丁目30番2号
 ⑳ 代 理 人 弁理士 猿渡 章雄 外1名

明 細 書

1. 発明の名称

液晶素子の製造方法

2. 特許請求の範囲

1. それぞれ一面に電極を形成した一対の電極基板を、それぞれの電極形成面を内側にして対向配置し、周縁部を接着剤により接着固定して液晶表示用セルを形成するに際して、少なくとも一方の基板の中央部において、スペーサ部材を形成した後、接着剤を印刷し、周縁部に設けた接着剤とともに一対の電極基板を接着固定することを特徴とする液晶素子の製造方法。

2. 前記スペーサ部材を、一様な成膜ならびにその部分的除去工程を含むリソグラフィ技術により形成する特許請求の範囲第1項に記載の液晶素子の製造方法。

3. 基板中央部に形成する接着剤およびスペーサ部材がいずれもポリイミド系樹脂からなる特許請求の範囲第1項または第2項に記載の液晶素子の製造方法。

3. 発明の詳細な説明

技術分野

本発明は、液晶表示装置におけるセルの製法に関するもので、特に1~2μmというように微小な間隙を必要とする液晶表示用セルの製法に関するものである。

背景技術

従来、液晶表示装置に使用されるセルは、第1図に示すように、それぞれ透明電極11a、11bを設けたガラス板等からなる一対の透明基板12a、12bを、それぞれの電極形成面を内側にして対向配置し、周縁部においてエポキシ系樹脂接着剤等の接着剤13により接着固定した構成を有する。その際、透明基板間に液晶を封入すべき空間14を与えるための間隔を保持するために、前記接着剤13中にガラス微細粉砕物、Al₂O₃粉末等で、所定の大きさを有するものからなるギャップ制御材を予め適量混入することによって、セル間隔を制御したり、前記接着剤をスクリーン印刷等の方法で透明基板上に形成した

り、上記ポリイミドを30℃に加熱したピロリドン：NaOH3%溶液＝4：3混合液に5～15分間浸漬してポリイミドをエッチングした後、レジストを剝離してストライプ状のスペーサ25を形成した。

その後再び、上記のように、γ-(2-アミノエチル)アミノプロピトリメトキシシランのnブタノール0.3wt%溶液を基板全面に塗布し硬化させた後に、上記ポリイミド前駆体SP-510をスクリーン印刷もしくは、オフセット印刷法により、ストライプ26および27のように印刷した。

他方、対向基板22aは、ITO電極21a上に厚さ400～500Åのポリイミド膜28を形成し、ラビング処理したものであって、これを上記のように接着剤を印刷した基板22bと位置合せした後、接着を行ない、4.0kg/cm²程度の圧力でプレスしつつ、240℃で3時間焼成した。

これにより、2μmの均一な基板間隔を有する

第3図に示すようなセルが得られた。

例2

上記例1の方法においては、上下ガラス基板を、ポリイミド接着剤26および27のみによって接着している。このため、プレスの際のガラス基板に働らく応力や歪の解消によって、剝離が生じ易い欠点がある。

これを避けるために、この例では、一旦、基板22b上にポリイミドによるストライプ状接着剤26のみを印刷し、更に対向基板22aと組合せて加圧下に焼成し、両基板を接着固定した後、更に周縁部にエポキシ系接着剤27を塗布し硬化させて、補強ならびにシールする構造を取った。この例ではエポキシ系接着剤27による補強を両基板をプレスしつつ行なったが、プレスを開放した状態で行なうことも可能である。

発明の効果

以上説明したように、本発明によれば、基板間隔が1～2μm程度というように微小である液晶表示用セルを形成するに際して、基板中央部にス

ペーサ部材を形成した後、接着剤を印刷し、周縁部の接着剤とともに接着固定する構成を取ることにより、中央に設けた接着剤を接着剤兼スペーサ部材として機能させることができ、基板間隔が1～2μm程度と微小な場合であっても、均一で安定な基板間隔を有する液晶表示用セルを製造する方法が提供される。

4. 図面の簡単な説明

第1図は従来の液晶表示セルの厚さ方向断面図、第2図は本発明方法に従う液晶表示セル製造過程を説明するための斜視図、第3図は得られる液晶表示セルの一例の厚さ方向断面図である。

11a、11b、21a、21b・・・透明電極

22a、22b・・・透明基板

25・・・スペーサ部材

26・・・中央部接着剤


13、27・・・周縁部接着剤

代表図面：第2図

出願人代理人 狼 旗 章 雄



第1図



第2図

